
COLORAMA DIMOUT

- Exclusive Colorama dimout fabric with colour matched reverse for a uniform appearance inside and out
- Cradle to Cradle Certified™ Bronze
- Standard 100 by Oeko-Tex® certified, free from harmful substances
- Washable up to 72°
- Proven acoustic properties



APPLICATIONS

FABRIC PROPERTIES

	Dimout
	Polyester
	350 g/m²
	0.80 mm
max.	305 cm
	310 cm

FEATURES / TECHNICAL PROPERTIES

	5
	Alpha-w = 0.60 / 0.80
	Flame retardant
	Applicable in humid areas
	Fabric must be turned
	Fabric must be turned
	Oeko-Tex, Cradle to Cradle
	Special colours from 240 m

WASHING INSTRUCTIONS

30 -0.5% 60 -1% 72 -2% -0.25%

FIRE PROTECTION

Class 1 (EN 13773)
Type B (BS 5867-2)

OEKO TEX® STANDARD 100 S08-0170 Hohenstein HTTI

cradle to cradle CERTIFIED BRONZE

More information
silentgliss.com

Colorama Dimout

OPTICAL AND SOLAR COEFFICIENTS (± 5%, DIN EN 410)

Colour	T_V	T_S	R_S	A_S	F_C	g_{tot}
408	0.1	0.1	31.3	68.6	0.72	0.52
409	0.0	0.1	18.0	81.9	0.80	0.58
410	0.0	0.1	27.4	72.5	0.74	0.54
411	0.0	0.1	20.9	79.0	0.79	0.57
422	0.0	0.1	23.2	76.7	0.77	0.55
429	0.0	0.1	26.2	73.7	0.75	0.54
446	0.0	0.1	19.7	80.2	0.79	0.57
463	0.1	0.1	29.9	70.0	0.73	0.52
478	0.0	0.1	21.0	78.9	0.78	0.57
479	0.0	0.1	25.3	74.6	0.76	0.55

T_V Visible light transmission
T_S Solar transmission
R_S Solar reflectance
A_S Solar absorption
F_C Shading factor
g_{tot} Total g-value

Fc + gtot: Value calculated with glass: 0.72 / Ug = 1.6 W/m² K, DIN EN 13363-1

Colorama Dimout


408


409


410


411


422


429


446


463


478


479

Colours shown are not binding

28/03/24