LEVISO LIGHT

- Subtly textured dimout fabric with a soft finished form
- Standard 100 by Oeko-Tex® certified, free from harmful substances
- Washable up to 60°
- Proven acoustic properties



APPLICATIONS

FABRIC PROPERTIES

Dimout	
Polyester	
300 g/m²	
0.62 mm	
295 cm	
300 cm	

FEATURES / TECHNICAL PROPERTIES

4-5	
Alpha-w = 0.80	
Flame retardant	
Fabric must be turned	
Fabric must be turned	
Oeko-Tex	
Special colours from 400 m	

WASHING INSTRUCTIONS

-0.5% -1% -0.25%

FIRE PROTECTION

Class 1 (EN 13773)
M1 (NF P 92-503/5/7)
Type B (BS 5867-2)

OEKO TEX® STANDARD 100 S08-0170 Hohenstein HTTI

More information
silentgliss.com

Leviso Light

OPTICAL AND SOLAR COEFFICIENTS (± 5%, DIN EN 410)

Colour	T_V	T_S	R_S	A_S	F_C	g_{tot}
1	0.6	1.0	59.8	39.2	0.54	0.39
2	0.6	1.0	59.8	39.2	0.54	0.39
3	0.6	1.0	59.8	39.2	0.54	0.39
8	0.6	1.0	59.8	39.2	0.54	0.39
9	0.0	0.8	44.5	54.7	0.64	0.46
11	0.0	0.8	44.5	54.7	0.64	0.46
12	0.0	0.8	44.5	54.7	0.64	0.46
14	0.0	0.9	37.1	62.0	0.68	0.49
17	0.0	0.8	44.5	54.7	0.64	0.46
18	0.0	0.9	37.1	62.0	0.68	0.49
19	0.0	0.9	37.1	62.0	0.68	0.49
23	0.0	0.9	37.1	62.0	0.68	0.49
25	0.0	0.9	37.1	62.0	0.68	0.49
27	0.6	1.0	59.8	39.2	0.54	0.39
28	0.0	0.9	37.1	62.0	0.68	0.49
29	0.0	0.9	34.0	65.1	0.70	0.51
30	0.0	0.9	34.0	65.1	0.70	0.51
31	0.0	0.9	37.1	62.0	0.68	0.49
32	0.0	0.8	44.5	54.7	0.64	0.46
33	0.6	1.0	59.8	39.2	0.54	0.39

T_V Visible light transmission
R_S Solar reflectance
F_C Shading factor
T_S Solar transmission
A_S Solar absorption
g_{tot} Total g-value

Fc + gtot: Value calculated with glass: 0.72 / Ug = 1.6 W/m² K, DIN EN 13363-1

Leviso Light


1


2


3


8


9


11


12


14


17


18


19


23


25


27


28


29


30


31


32


33

Colours shown are not binding